

RoHS TEST REPORT

Report Number	KTi250613R863
Applicant	Wenzhou Changting Plastic Products Co., Ltd.
Address	No. 21 Xingni Road, Wanquan Town, Pingyang County, Wenzhou City, Zhejiang Province, China
Manufacture	Wenzhou Changting Plastic Products Co., Ltd.
Address	No. 21 Xingni Road, Wanquan Town, Pingyang County, Wenzhou City, Zhejiang Province, China
Sample Name	COSMETIE MIRROR
Model	XR-2328
Date of Receipt	Jun. 14, 2025
Date of Test	Jun. 15, 2025 To Jun. 19, 2025
Date of Report	Jun. 24, 2025
Test laboratory	Guangdong KAIXU Testing Technology Co., Ltd.
Test location	Room 215, Building 2, No. 123, Dongcheng Section, Guanlong Road, Dongcheng Street, Dongguan City, Guangdong Province, China

Test Conclusion:

Test Requested	Conclusion
As specified by client, to determine the Lead(Pb), Cadmium(Cd), Mercury(Hg), Hexavalent chromium(Cr ⁶⁺), Polybrominated Biphenyls(PBBs), Polybrominated Diphenyl Ethers(PBDEs), Dibutyl phthalate (DBP), Butyl benzyl phthalate(BBP), Bis(2-ethylhexyl) phthalate (DEHP) and Diisobutyl phthalate (DIBP) content in the submitted sample(s) in accordance with EU directive 2011/65/EU and revised directive (EU)2015/863 (RoHS2.0) .	PASS

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of KAIXU Test International

Tested by: Cathy

Approved by: Martin

Test Method:

1. With reference to IEC 62321-2:2013, review was performed for the samples disjointed from the submitted articles.
2. With reference to IEC 62321-1:2013, tests were performed for the samples indicated by the photos in this report
 - (1) With reference to IEC 62321-3-1:2013, screening by XRF spectroscopy.
 - (2) Wet chemical test method
 - a. With reference to IEC 62321-5:2013, determination of Cadmium by ICP-OES.
 - b. With reference to IEC 62321-5:2013, determination of Lead by ICP-OES.
 - c. With reference to IEC 62321-4:2013+A1:2017, determination of Mercury by ICP-OES.
 - d. With reference to IEC 62321-7-1:2015 & IEC 62321-7-2:2017, determination of Hexavalent chromium by Colorimetric method using UV-Vis.
 - e. With reference to IEC 62321-6:2015, determination of PBBs and PBDEs by GC-MS.
3. With reference to IEC 62321-8: 2017, determination of phthalates by GC-MS.

Test Result:

Item	Results of XRF ⁽¹⁾ (mg/kg)					Results of Wet Chemical Test ⁽²⁾ (mg/kg)						
	Pb	Cd	Hg	Cr	Br	Cr ⁶⁺	PBBs	PBDEs	DBP	BBP	DEHP	DIBP
Limit	1000	100	1000	1000	1000	1000	1000	1000	1000	1000	1000	1000
No.												
1	BL	BL	BL	BL	--	--	--	--	--	--	--	--
2	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
3	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
4	BL	BL	BL	X	--	NEG	--	--	--	--	--	--
5	BL	BL	BL	BL	--	--	--	--	--	--	--	--
6	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
7	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
8	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
9	BL	BL	BL	BL	--	--	--	--	--	--	--	--
10	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
11	BL	BL	BL	BL	--	--	--	--	--	--	--	--
12	BL	BL	BL	BL	--	--	--	--	--	--	--	--
13	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
14	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
15	BL	BL	BL	BL	--	--	--	--	--	--	--	--
16	BL	BL	BL	BL	X	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
17	BL	BL	BL	X	--	NEG	--	--	--	--	--	--
18	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
19	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.

This test report is limited to the above client company and the product model only. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 30 days only. It may not be duplicated without prior written consent of Guangdong KAI XU Testing Technology Co., Ltd.

Item	Results of XRF ⁽¹⁾ (mg/kg)					Results of Wet Chemical Test ⁽²⁾ (mg/kg)						
	Pb	Cd	Hg	Cr	Br	Cr ⁶⁺	PBBs	PBDEs	DBP	BBP	DEHP	DIBP
Limit	1000	100	1000	1000	1000	1000	1000	1000	1000	1000	1000	1000
No.												
20	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
21	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
22	BL	BL	BL	BL	BL	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
23	BL	BL	BL	BL	--	--	--	--	--	--	--	--
24	BL	BL	BL	BL	--	--	--	--	--	--	--	--

This test report is limited to the above client company and the product model only. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 30 days only. It may not be duplicated without prior written consent of Guangdong KAIXU Testing Technology Co., Ltd.

Remark:

(1)

- Pb=Lead,
- Cd=Cadmium,
- Hg=Mercury,
- Cr=Chromium,
- Br=Bromine,
- PBBs=Polybrominated biphenyls,
- PBDEs=Polybrominated diphenyl ethers.

(2)

- (a) It is the result on total Br while test item on restricted substances is PBBs/PBDEs. It is the result on total Cr while test item on restricted substances is Cr⁶⁺.
- (b) Results are obtained by XRF for primary screening, and further chemical testing by ICP-OES (for Cd, Pb,Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) is recommended to be performed, if the concentration exceeds the below warning value according to IEC62321-3-1:2013(unit: mg/kg).

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ< X <130+3σ≤OL	BL≤70-3σ< X <130+3σ≤OL	BL≤50-3σ< X <150+3σ≤OL
Pb	mg/kg	BL≤700-3σ< X <1300+3σ≤OL	BL≤700-3σ< X <1300+3σ≤ OL	BL≤500-3σ< X <1500+3σ≤OL
Hg	mg/kg	BL≤700-3σ< X <1300+3σ≤OL	BL≤700-3σ< X <1300+3σ≤OL	BL≤500-3σ< X <1500+3σ≤OL
Cr	mg/kg	BL≤700-3σ< X	BL≤700-3σ< X	BL≤500-3σ< X
Br	mg/kg	BL≤300-3σ< X	--	BL≤250-3σ< X

- (c) OL=Over Limit, BL=Below Limit, X=inconclusive, LOD=Limit of Detection, NA=not applicable
- (d) The XRF screening test for RoHS elements-The reading may be different to the actual content in the sample be of non-uniformity composition

(3)

- (a) mg/kg=ppm=0.0001%, N.D.=not detected(<MDL), NEG= Negative
- (b) Unit and Method Detection Limit (MDL) in wet chemical test

Test Items	Pb	Hg	Cd	PBBs	PBDEs	DBP	BBP	DEHP	DIBP
Unit	mg/kg								
MDL	10	10	10	50	50	50	50	50	50

The MDL for single compound of PBBs &PBDEs is 50mg/kg, MDL of Cr⁶⁺ for metal sample is 0.10µg/cm² and MDL of Cr⁶⁺ for polymer & composite sample is 8mg/kg.

(c) Metal sample:


	CrVI concentration	Conclusion
1	> 0.13 µg/cm ²	Positive
2	< 0.10 µg/cm ²	Negative
3	0.10 µg/cm ² ~ 0.13 µg/cm ²	Inconclusive

unavoidable coating variations may influence the determination


Information on storage conditions and production date of the tested sample is unavailable and thus Cr⁶⁺ results represent status of the sample at the time of testing.

Appendix I**Test Process:**

1. Test for Cd/Pb Content




2. Test for Hg Content




3. Test for Chromium (VI) Content


Soluble polymers:




Insoluble/unknown polymers and electronics without Sb



Metal material




4. Test for DBP, BBP, DEHP, DIBP, PBBs, PBDEs Content




Sample Description:

Material No.	Description
1	Mirror
2	White Plastic Shell
3	Black Plastic Shell
4	Silver Metal Tube
5	Battery
6	Black Wire Skin
7	Red Wire Skin
8	White Wire Skin
9	Wire Core
10	White Plastic Shell
11	USB Plug
12	USB-C Plug
13	Flexible Circuit Board
14	Led Lamp Beads
15	Copper Foil
16	Green PCB
17	Silver Metal Spring
18	IC
19	Capacitor
20	Resistance
21	Diode
22	Transistor
23	Soldering
24	USB-C Interface

Tested sample photos





-----THE END OF REPORT-----